

**DE** Stand 02.2025 | Revision N

## Produktdatenblatt Technische Daten

## FINETT OFFICE

Nutzschicht	100 % Polyamid solution dyed														
Rücken	Textilrücken (Vlies)														
GWP (EPD A1-A3)	8,26 kg CO <sub>2</sub> -Äq./m <sup>2</sup>														
Recyclinganteil prEN 17903	36 %														
Produktpass Nachhaltigkeit	119-1-22008.1														
Emissionsgeprüft nach TÜV PROFICERT   CRI-Grundsätzen	70 710 6625-1 (PREMIUM)														
Gesundheitliche Unbedenklichkeit Umweltzeichen RAL-UZ 128	BLAUER ENGEL Vertrag Nr. 19794														
DGNB Kriterium ENV 1.2	Qualitätsstufe 4 (QS 4)														
REACH Verordnung Nr. 1907/2006 Artikel 33	enthält keine Stoffe aus der SVHC-Liste, die nach Artikel 33 deklariert werden müssen														
Flächengewicht ISO 8543	1320 g/m <sup>2</sup>														
Nutzschichteinsatzgewicht	540 g/m <sup>2</sup>														
Flächengewicht der Nutzschicht EN 984	500 g/m <sup>2</sup>														
Gesamtdicke ISO 1765	5,5 mm														
Abmessungen	Rollenbreite 200 cm   Rollenlänge 25-35 lfm   Stanzlinge (zur dauerhaften Verklebung) 61 x 61 cm														
Beanspruchungsbereich EN 1307	Klasse 33   Geschäftsbereich stark														
Lichtechtheit EN ISO 105-B02	6														
Brandverhalten EN 13501-1	C <sub>fi</sub> – s1														
Quelllufteignung	-														
Gleitwiderstand EN 13893	DS (> 0,30)														
Wärmedurchlasswiderstand ISO 8302	0,09 m <sup>2</sup> K/W geeignet für Fußbodenheizung														
Trittschallminderung EN ISO 10140-3	21 dB														
Schallabsorptionsgrad EN ISO 354	<table border="1"> <thead> <tr> <th>Freq. Hz</th> <th>125</th> <th>250</th> <th>500</th> <th>1000</th> <th>2000</th> <th>4000</th> </tr> </thead> <tbody> <tr> <td>α<sub>s</sub></td> <td>0,03</td> <td>0,03</td> <td>0,07</td> <td>0,14</td> <td>0,36</td> <td>0,53</td> </tr> </tbody> </table>	Freq. Hz	125	250	500	1000	2000	4000	α <sub>s</sub>	0,03	0,03	0,07	0,14	0,36	0,53
Freq. Hz	125	250	500	1000	2000	4000									
α <sub>s</sub>	0,03	0,03	0,07	0,14	0,36	0,53									
Elektrostatische Grenzaufladung ISO 6356	≤ 2,0 kV														
Erdableitwiderstand EN 61340-4-1 (leitfähig verlegt - die Hinweise des Verlegewerk- stofflieferanten sind ebenfalls zu beachten)	-														
Sonderfarben	> 2500 m <sup>2</sup>														
Verlegung DIN 18365															

Vollflächige Verklebung mit Klebstoffen der niedrigsten Emissionsklasse, frei von niedrig-, mittel und hoch siedenden Lösungsmitteln und mit einer hart-elastischen Kleberfuge (Zugscherfestigkeit ≥ 2 N/mm<sup>2</sup>, Prüfung nach DIN EN ISO 17178). Siehe Verlegeanleitung für dauerhaft verklebte Bahnenware und dauerhaft verklebte Stanzlinge.



**Bitte beachten Sie auch die Hinweise auf der Folgeseite!**

**DE** Stand 02.2025 | Revision N

**Produktdatenblatt  
Technische Daten**

**FINETT OFFICE**

Fordern Sie unbedingt vor der Bestellung ein größeres Muster zur Beurteilung der Farbwirkung an.

Produktionsbedingte Farbunterschiede zwischen Muster und Fertigware sowie technische Veränderungen, die der Produktverbesserung dienen, behalten wir uns vor. Unsere Verlegeanleitungen sowie unsere Reinigungs- und Pflegeanleitung sind zu beachten.

Traditionelle Nadelvlies-Bodenbeläge bestehen aus einer Mischung verschiedenfarbiger Grobfasern, die beim fertigen Produkt für die typische, melierte Optik sorgen.

Wie bei anderen Materialien gilt auch bei Nadelvlies: Gedeckte und melierte Farben kaschieren mögliche Verschmutzungen besser als helle und farbintensive Uni-Töne. Durch die Wahl unempfindlicher Farbkombinationen lassen sich die notwendigen Reinigungsintervalle\* entsprechend verlängern.

Geringfügige optische Unregelmäßigkeiten im Warenbild (z. B. durch Fremdfasern) sowie Farbabweichungen im Sinne von Kapitel 2.8 des aktuellen Kommentars zur DIN 18365 sind produktionsbedingt nicht immer zu vermeiden und stellen keinen Mangel\*\* dar.

\*Siehe auch unsere Reinigungs- und Pflegeanleitung bzw. den aktuellen Kommentar zur DIN 18365: „Voraussetzung für die Eignung des Bodenbelags sind eine auf die Beanspruchung abgestimmte Reinigung und Pflege (Werterhaltung), ausreichende Sauberlaufzonen und die nutzungsrelevante Berücksichtigung der Farbgebung.“

\*\*Die Pflichten des Verarbeiters nach § 377 HGB bleiben hiervon unberührt.



[www.blauer-engel.de/luz128](http://www.blauer-engel.de/luz128)



**EN** date of issue 02.2025 | revision N

## Technical data sheet

Wear layer  
 Backing  
 GWP (EPD A1-A3)  
 Recycled content prEN 17903  
 Product passport sustainability  
 Emission tested acc. to TÜV PROFICERT | acc. to CRI-principles  
 Health safety Environmental label RAL-UZ 128  
 DGNB criterion ENV 1.2  
 REACH regulation No. 1907/2006 article 33  
 Total weight ISO 8543  
 Fiber weight  
 Wear layer weight EN 984  
 Total thickness ISO 1765  
 Dimensions  
 Level of use EN 1307  
 Colour fastness to light EN ISO 105-B02  
 Fire rating EN 13501-1  
 Suitable for under-floor air supply  
 Slipperiness EN 13893  
 Thermal resistance ISO 8302  
 Impact sound insulation EN ISO 10140-3  
 Sound absorption EN ISO 354  
 Anti-static ISO 6356  
 Resistance to earth EN 61340-4-1 (installed conductively - the instructions of the supplier of the installation materials should also be observed)  
 Special colours  
 Installation DIN 18365

## FINETT OFFICE

100 % polyamide solution dyed  
 Textile backing (non-woven fabric)  
 8,26 kg CO<sub>2</sub>-Eq./m<sup>2</sup>  
 36 %  
 119-1-22008.1  
 70 710 6625-1 (PREMIUM)  
 BLUE ANGEL Contract No. 19794  
 Quality Level 4 (QL 4)  
 does not contain any substances from the SVHC list which have to be declared according to article 33  
 1320 g/m<sup>2</sup>  
 540 g/m<sup>2</sup>  
 500 g/m<sup>2</sup>  
 5,5 mm  
 Roll width 200 cm | Roll length 25-35 m | Raised floor cuts (for permanent adhesion): 61 x 61 cm  
 class 33 | commercial heavy  
 6  
 CfI – s1  
 -  
 DS (> 0,30)  
 0,09 m<sup>2</sup> K/W suitable for underfloor heating  
 21 dB  

Freq. Hz	125	250	500	1000	2000	4000
α <sub>s</sub>	0,03	0,03	0,07	0,14	0,36	0,53

 ≤ 2,0 kV  
 -  
 > 2500 m<sup>2</sup>

For the correct installation of our textile floorings use only ultra low emission adhesives, free of low-, middle- a high boiling solvents and with a high strength (≥ 2 N/mm<sup>2</sup>, in accordance with DIN EN ISO 17178). Please consult our installation instructions for permanently glued rolls and permanently glued raised floor cuts.



Please also note the information on the following page!

**EN** date of issue 02.2025 | revision N

**Technical data sheet**

**FINETT OFFICE**

We highly recommend to ask for a larger sample before placing your order. Subject to product improvements and usual colour deviations. Please also consult our installation and cleaning maintenance instructions.

Traditional needled carpets consist of a mixture of coloured coarse fibers, which give the finished product the typical mottled look.

As with other materials, the same applies to needled carpets: covered and mottled colours hide possible stains better than bright and colourful uni shades. By choosing less sensitive colour combinations, the necessary cleaning intervals\* can be extended accordingly.

Minor optical irregularities in the appearance of the product (for example non-matching fibers) as well as colour deviations in the sense of chapter 2.8 of the current commentary on DIN 18365 can not always be avoided due to the production process and are not a defect\*\*.

\*See also our cleaning and care instructions or the current commentary to DIN 18365: "Precondition for the suitability of the floor covering is a cleaning and care (value retention) tailored to the load, sufficient clean-up zones and the usage-relevant consideration of the colour scheme."

\*\*The obligations of the processor according § 377 HGB remain unaffected.

